



Owner: Knauf A/S
No.: MD-21087-EN
Issued: 11-02-2022
Valid to: 11-02-2027

3rd PARTY **VERIFIED**

EPD

VERIFIED ENVIRONMENTAL PRODUCT DECLARATION | ISO 14025 & EN 15804







Owner of declaration

Knauf A/S Kløvermarksvej 6 DK-9500 Hobro CVR: 5405 0313



Programme

EPD Danmark

www.epddanmark.dk

Kepddanmark

 $\ \square$ Industry EPD

☑ Product EPD

Declared product(s)

Classic Board

Number of declared datasets/product variations: 1

The Knauf Classic Board is a glass fiber reinforced gypsum plasterboard. The EPD is valid for all variations carrying the Knauf Classic 1 Board and Knauf Danogips Classic 3 Board name. The range includes products with different edge profiles such as tapered, square and beveled edges.

The calculations cover similar products (variation <5%) and are based on the product with the highest environmental impact within the product group (article number 11990).

Production site

Knauf's production site in Hobro; Kløvermarksvej 6, DK-9500 Hobro, Denmark

Product use

The product is used for general indoor building construction of walls and ceilings.

Declared/ functional unit

 1 m^2

Year of data

2019

Issued: 11-02-2022

Valid to:

11-02-2027

Basis of calculation

This EPD is developed in accordance with the European standard EN 15804+A2.

Comparability

EPDs of construction products may not be comparable if they do not comply with the requirements in EN 15804. EPD data may not be comparable if the datasets used are not developed in accordance with EN 15804 and if the background systems are not based on the same database.

Validity

This EPD has been verified in accordance with ISO 14025 and is valid for 5 years from the date of issue.

Use

The intended use of an EPD is to communicate scientifically based environmental information for construction products, for the purpose of assessing the environmental performance of buildings.

EPD type

□Cradle-to-gate with modules C1-C4 and D

□Cradle-to-grave and module D □Cradle-to-gate

□Cradle-to-gate with options

CEN standard EN 15804 serves as the core PCR

Independent verification of the declaration and data, according to EN ISO 14025

☐ internal

Third party verifier:

Ninkie Bendtsen

Martha Katrine Sørensen

Life	Life cycle stages and modules (MND = module not declared)															
Product Construction process				Use					End of life			Beyond the system boundary				
Raw material supply	Transport	Manufacturing	Transport	Installation process	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Re-use, recovery and recycling potential
A1	A2	А3	A4	A5	B1	B2	В3	B4	B5	В6	В7	C1	C2	С3	C4	D
X	X	X	X	MND	MND	MND	MND	MND	MND	MND	MND	X	X	X	X	x





Product information

Product description

The main product components and packaging are shown in the tables below.

Material	Weight-% of declared product
Paper	4%
Stucco	87%
Fibre glass	<1%
Additives	<1%
Glue	<1%
Water	8%

Packaging	Weight-%
Ceiling_board	99.1%
PE film	0.9%

Representativity

This declaration, including data collection and the modeled foreground system including results, represents the production of gypsum board on the production site located in Hobro. Product specific data are based on average values collected in the period 2019. Background data are based on the GaBi 2021.2 database and are less than 10 years old except for two detergents <0.05% (w/w). Generally, the used background datasets are of high quality, and the majority of the datasets are only a couple of years old.

Hazardous substances

Knauf Classic boards do not contain substances listed in the "Candidate List of Substances of Very High Concern for authorisation"

(http://echa.europa.eu/candidate-list-table)

Essential characteristics

According to EN 520:2009 the Classic Board is classified as type A (plasterboard with a face to which suitable gypsum plasters or decoration may be applied).

Further technical information can be obtained by contacting Knauf or on the website: www.knauf.dk

Reference Service Life (RSL)

The RSL is defined as 60 years according to NPCR 010 version 3.0.









LCA background

Declared unit

The LCI and LCIA results in this EPD relates to 1 $\mbox{m2}$

Name	Value	Unit
Declared unit	1	m ²
Area density	8.3	kg/m²
Conversion factor to 1 kg.	0.120	-


Not defined

PCR

This EPD is developed according to the core rules for the product category of construction products in EN 15804, and NPCR 010 version 3.0.

Flowdiagram

The diagram below shows the system boundaries of the EPD. A detailed illustration of A3 is shown later.







System boundary

This EPD is based on an LCA including cradle-to-gate with options, modules C1-C4, and module D. 100 % (w/w) of the product has been accounted for.

The general rules for the exclusion of inputs and outputs follows the requirements in EN 15804, 6.3.5, where the total of neglected input flows per module shall be a maximum of 5 % of energy usage and mass for unit processes.

Product stage (A1-A3) includes:

The product stage comprises the acquisition of all raw materials, products and energy, transport to the production site, packaging and waste processing up to the "end-of-waste" state or final disposal. The LCA results are declared in aggregated form for the product stage, which means, that the sub-modules A1, A2 and A3 are declared as one module A1-A3.

A1 – Extraction and processing of raw materials The raw gypsum is mined in Spain. All other raw materials are produced mainly in Northern Europe.

A2 - Transport to the production site

The inbound transport includes all incoming material from suppliers. This includes the transport of Flue-Gas Desulfurization (FGD) from coal-based power plants, as well as transport of raw natural gypsum from Spain.

A3 - Manufacturing processes

The natural, recycled or FGD based gypsum is heated/calcinated to bring the gypsum to the

hemihydrate state known as stucco. The stucco is mixed with water and other additives and sandwiched between the front and back liner. After initial hardening, the plates are cut into shape and heated in the curing oven.

Construction process stage (A4-A5) includes:

A weighted average for the transport distance of 237 km is included for the average Danish market situation.

The installation phase (A5) is not included.

Use stage (B1-B7) includes:

Not included

End of Life (C1-C4) includes:


The board is dismantled by hand (C1) and transported to municipal collection facilities, and from here to a recycling company (C2).

The gypsum part of the plate (gypsum and additives) is split from the paper liners using electricity-based machinery (C3). The paper part is assumed incinerated with energy recovery (C4)

Re-use, recovery and recycling potential (D) includes:

The gypsum part of the product is recycled as gypsum and avoids mining and production of natural gypsum. This can be done at Knauf and recycled in new Knauf boards.

The recovered energy from incineration of paper avoids the production of primary heat or electricity at power plants.







LCA results

The LCIA results are calculate using GaBi 10.6 with database version 2021.2, and using the characterization model defined in GaBi as EN15804+A2 for classifying and characterizing input and output flows.

	ENVIRONMENTAL EFFECTS PER PRODUKT PER M ²								
Parameter	Enhed	A1-A3	A4	C1	C2	C3	C4	D	
GWP-total	[kg CO₂ eq.]	1.23E+00	1.56E-01	0.00E+00	1.28E-01	3.70E-02	4.71E-01	-1.72E-01	
GWP-fossil	[kg CO₂ eq.]	1.79E+00	1.53E-01	0.00E+00	1.25E-01	3.67E-02	1.17E-02	-1.71E-01	
GWP-bio	[kg CO₂ eq.]	-5.62E-01	1.65E-03	0.00E+00	1.35E-03	3.12E-04	4.59E-01	-8.53E-04	
GWP-luluc	[kg CO₂ eq.]	1.57E-03	1.26E-03	0.00E+00	1.04E-03	5.19E-05	8.05E-06	-1.37E-04	
ODP	[kg CFC 11 eq.]	4.13E-09	3.05E-17	0.00E+00	2.51E-17	8.78E-16	9.06E-17	-1.96E-15	
AP	[mol H ⁺ eq.]	4.04E-03	1.68E-04	0.00E+00	1.37E-04	7.63E-05	1.31E-04	-2.55E-04	
EP-fw	[kg P eq.]	3.82E-05	4.60E-07	0.00E+00	3.77E-07	9.83E-08	1.64E-08	-2.31E-07	
EP-mar	[kg N eq.]	1.77E-03	5.42E-05	0.00E+00	4.45E-05	1.81E-05	4.75E-05	-7.95E-05	
EP-ter	[mol N eq.]	1.89E-02	6.42E-04	0.00E+00	5.27E-04	1.90E-04	5.93E-04	-8.63E-04	
POCP	[kg NMVOC eq.]	5.03E-03	1.46E-04	0.00E+00	1.20E-04	4.92E-05	1.26E-04	-2.23E-04	
ADP-mm ¹	[kg Sb eq.]	1.38E-06	1.37E-08	0.00E+00	1.13E-08	1.08E-08	1.39E-09	-2.87E-08	
ADP-fos ¹	[MJ]	2.84E+01	2.06E+00	0.00E+00	1.69E+00	6.52E-01	1.50E-01	-2.94E+00	
WDP ¹	[m³]	2.94E-01	1.44E-03	0.00E+00	1.18E-03	5.88E-03	5.82E-02	-1.28E-02	
Caption	GWP-total = Globale War Warming Potential - bio Depletion; AP = Acidifcatio marine; EP-terrestrial = E Potential – mine	genic; GWP-lu n; EP-freshwa utrophication	luc = Global \ ater = Eutropl – terrestrial;	Warming Pote nication – aqu POCP = Photo	ntial - land us atic freshwate ochemical zone	e and land us er; EP-marine e formation; A	e change; OD = Eutrophicat ADPm = Abiot	P = Ozone ion – aquatic tic Depletion	
Disclaimer	¹ The results of this environ				e as the unce ith the indicat		ese results ar	e high or as	

	ADDITIONAL ENVIRONMENTAL EFFECTS PER PRODUKT PER M ²									
Parameter	Enhed	A1-A3	A4	C1	C2	C3	C4	D		
PM	[Disease incidence]	8.08E-08	1.14E-09	0.00E+00	9.31E-10	6.43E-10	7.21E-10	-3.49E-08		
IRP2	[kBq U235 eq.]	4.33E-02	5.49E-04	0.00E+00	4.50E-04	1.59E-02	1.18E-03	-3.45E-02		
ETP-fw1	[CTUe]	5.49E+00	1.53E+00	0.00E+00	1.25E+00	2.74E-01	7.03E-02	-6.44E-01		
HTP-c1	[CTUh]	6.43E-10	3.09E-11	0.00E+00	2.54E-11	7.77E-12	3.79E-12	-2.84E-11		
HTP-nc1	[CTUh]	7.49E-09	1.61E-09	0.00E+00	1.32E-09	2.93E-10	1.68E-10	-1.15E-09		
SQP1	-	8.46E+00	7.08E-01	0.00E+00	5.81E-01	2.06E-01	3.91E-02	-4.94E-01		
Caption	PM = Particulate Matter emissions; IRP = Ionizing radiation – human health; ETP-fw = Eco toxicity – freshwater; HTP-c =									
Сарион	Human toxicity – cancer									
Disclaimers	¹ The results of this environ						ese results are	high or as		
Discidifficis		ther	e is limited ex	perienced wit	th the indicato	r.				
	² This impact category de	eals mainly wi	th the eventu	al impact of lo	ow dose ionizi	ng radiation o	n human hea	Ith of the		
	nuclear fuel cycle. It doe									
	radioactive waste disposal i	n undergroun	d facilities. Po	tential ionizin	g radiation fro	om the soil, fr	om radon and	from some		
		constructio	n materials is	also not meas	sured by this i	indicator.				

	RESSOURCE CONSUMPTION PER PRODUKT PER M ²								
Parameter	Enhed	A1-A3	A4	C1	C2	С3	C4	D	
PERE	[MJ]	4.36E+00	1.19E-01	0.00E+00	9.73E-02	3.01E-01	2.84E-02	-6.69E-01	
PERM	[MJ]	6.63E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	
PERT	[M]]	1.10E+01	1.19E-01	0.00E+00	9.73E-02	3.01E-01	2.84E-02	-6.69E-01	
PENRE	[MJ]	2.81E+01	2.07E+00	0.00E+00	1.70E+00	6.52E-01	1.50E-01	-2.95E+00	
PENRM	[M]]	3.45E-01	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	
PENRT	[MJ]	2.85E+01	2.07E+00	0.00E+00	1.70E+00	6.52E-01	1.50E-01	-2.95E+00	
SM	[kg]	5.07E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	
RSF	[MJ]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	
NRSF	[MJ]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	
FW	[m³]	1.13E-02	1.36E-04	0.00E+00	1.11E-04	2.93E-04	1.37E-03	-6.46E-04	
Caption	PERE = Use of renewable p Use of renewable primar resources; PENRE = Use o raw materials; PENRM = U non renewable primary er NRSF	ry energy reso f non renewal lse of non rene	urces used as ole primary en ewable primar es; SM = Use	raw material: lergy excluding ry energy reso of secondary	s; PERT = Tot g non renewa purces used as material; RSF	tal use of reneable primary e s raw material = Use of reneable	ewable primar nergy resourc ls; PENRT = T ewable second	y energy ses used as otal use of	





	WASTE CATEGORIES AND OUTPUT FLOWS PER PRODUKT PER M ²									
Parameter	Enhed	A1-A3	A4	C1	C2	C3	C4	D		
HWD	[kg]	3.98E-06	1.09E-10	0.00E+00	8.94E-11	1.72E-10	2.78E-11	-6.58E-10		
NHWD	[kg]	2.21E-02	3.25E-04	0.00E+00	2.66E-04	4.63E-04	1.48E-02	-1.38E-03		
RWD	[kg]	2.99E-04	3.75E-06	0.00E+00	3.08E-06	9.71E-05	7.61E-06	-2.11E-04		
CRU	[kg]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00		
MFR	[kg]	5.48E-03	0.00E+00	0.00E+00	0.00E+00	7.97E+00	0.00E+00	0.00E+00		
MER	[kg]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	3.32E-01	0.00E+00	0.00E+00		
EEE	[MJ]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	7.12E-01		
EET	[MJ]	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	1.29E+00		
HWD = Hazardous waste disposed; NHWD = Non hazardous waste disposed; RWD = Radioactive waste disposed							osed; CRU =			
Caption	Components for re-use; M	FR = Materials	for recycling	; MER = Mate	erials for energ	gy recovery; E	EE = Exporte	d electrical		
		ϵ	energy; EET =	Exported the	rmal energy					

BIOGENIC CARBON CONTENT PER PER PRODUKT PER M2							
Parameter	Unit	At the factory gate					
Biogenic carbon content in product	kg C	1.44E-01					
Biogenic carbon content in accompanying packaging	kg C	5.00E-02					





Additional information

Technical information on scenarios

Transport to the building site (A4)

Scenario information	Value	Unit
Fuel type	Diesel	-
Vehicle type	Truck, Euro 6, 28 - 32t gross weight / 22t payload capacity	-
Transport distance	237	km
Capacity utilisation (including empty runs)	61	%
Gross density of products transported	664	kg/m³
Capacity utilisation volume factor	1	-

Reference service life

RSL information	Unit		
Reference service Life	60 years		
Declared product properties			
Design application parameters			
Assumed quality of work	Information on the technical characteristics, design		
Outdoor environment	and construction guidelines, as well as conditions during use can be found on the website of Knauf at		
Indoor environment	www.knauf.dk		
Usage conditions]		
Maintenance			

End of life (C1-C4)

Scenario information	Value	Unit	
Collected separately	8.3	kg	
Collected with mixed waste	0	kg	
For reuse	0	kg	
For recycling	8.0	kg	
For energy recovery	0.3	kg	
For final disposal	0	kg	
Assumptions for scenario development	The gypsum part is assumed recycled and paper paincinerated		

Re-use, recovery and recycling potential (D)

Scenario information/Materiel	Value	Unit
Gypsum	8.0	kg
Electric energy	0.7	MJ
Thermal energy	1.3	MJ





Indoor air

The EPD does not give information on release of dangerous substances to indoor air because the horizontal standards on measurement of release of regulated dangerous substances from construction products using harmonised test methods according to the provisions of the respective technical committees for European product standards are not available.

Classic Board is covered by the Danish Indoor Climate Labelling, Certificate no. 009.

Soil and water

The EPD does not give information on release of dangerous substances to soil and water because the horizontal standards on measurement of release of regulated dangerous substances from construction products using harmonised test methods according to the provisions of the respective technical committees for European product standards are not available.





References

Publisher	L epddanmark
	www.epddanmark.dk
Programme operator	Danish Technological Institute Buildings & Environment Gregersensvej DK-2630 Taastrup www.teknologisk.dk
LCA-practitioner	Danish Technological Institute Buildings & Environment Gregersensvej DK-2630 Taastrup www.teknologisk.dk
LCA software /background data	Thinkstep GaBi 10.6 Database version 2021.2 www.gabi-software.com
3 rd party verifier	Ninkie Bendtsen NIRAS A/S Sortemosevej 19 DK-3450 Allerød www.niras.dk

General programme instructions

Version 2.0 www.epddanmark.dk

EN 15804

DS/EN 15804 + A2:2019 - "Sustainability of construction works - Environmental product declarations - Core rules for the product category of construction products"

NPCR 010 version 3.0.

NPCR 010 version 3.0. "PCR - Part B for Building boards"

EN 15942

DS/EN 15942:2011 – " Sustainability of construction works – Environmental product declarations – Communication format business-to-business"

ISO 14025

DS/EN ISO 14025:2010 – " Environmental labels and declarations – Type III environmental declarations – Principles and procedures"

ISO 14040

DS/EN ISO 14040:2008 – " Environmental management – Life cycle assessment – Principles and framework"

ISO 14044

DS/EN ISO 14044:2008 - " Environmental management - Life cycle assessment - Requirements and guidelines"